

ULTRALUBE® E-345

Product Description:

Ultralube® E-345 is a water based paraffin wax emulsion improving the surface qualities of aqueous lacquers and paints as well as leather lacquers and leather finishes.

Technical Data:

Form supplied	: white liquid
Solids type	: paraffin wax
Solids content	: 50% ± 1
pH	: 9.0 ± 0.5
Ionic character	: anionic
Melting range	: ~ 58-80°C

Properties:

Ultralube® E-345 is used in:

- * lacquers
- * paints
- * leather lacquers
- * leather finishes

Packaging:

- 115 kg drum - 950 kg IBC

Storage / Transport:

This product is stable for at least twelve months at temperatures of 5°C to 30°C.

!! Keep from freezing and temperatures higher than 30°C !!

Transport Classifications:

For further information please refer to the material safety data sheet.

Processing:

Ultralube® E-345 is stirred directly into the formulation. Long storage might cause phase separation because of different densities of water and paraffin.

Please stir before use!

Dosage:

1-4 % in reference to the entire formulation

in order to increase or improve:

- * water repellency
- * anti blocking
- * slip
- * mar and scuff resistance
- * soft touch

EEC-Labeling Requirements:

For further information please refer to the material safety data sheet.

FDA-/BfR-Regulations:

FDA : All raw materials used in Ultralube® E-345 fulfil the requirements of FDA 21, CFR 175.105, 176.170 and 176.180.

BfR : All raw materials used in Ultralube® E-345 fulfil the requirements of BfR XIV and XXXVI.

issue date: 14.03.2017
edition/supersedes: 11/16
revision: 5

All information given here are based on our own research or the research of others and believed to be accurate and shall give the user guidance for the application. Nevertheless these data are no specification and due to the versatile possible formulations, applications, processings and further parameters at the formulator/user the usage of this product has to be tested carefully in the particular system/application by the formulator/user. All information mentioned here are not warranted properties. There is no responsibility of the seller if the material is used outside the recommended field of use; any liability, also for any patent infringement, cannot be derived from this.