

Leneta Company, Inc.
 15 Whitney Rd.
 Mahwah, NJ, 07430 USA
Phone: 201.847.9300 • **Fax:** 201.848.8833
Email: sales@leneta.com • **Website:** www.leneta.com

Form P121-10N Leneta Scrub Test Panels

Black Plastic-Vinyl Chloride/Acetate Copolymer
Smooth Matte Surface - Plasticizer Free
Used in ASTM D 2486, ASTM D 4213, ISO 11998 and Other Scrub Test Methods

In a typical scrub test, the coating is applied to the Leneta Scrub Test Panel at a specified film thickness, allowed to dry, then subjected to scrubbing with a straight-line scrub tester. In ASTM D 2486, a 10 mil shim is inserted under the panel to accelerate failure and thereby reduce testing time. The scrub resistance is the number of scrub cycles required to remove the coating to a specified end point.

Alternatively, the loss in weight is determined after a specified number of scrub cycles as a measure of scrub resistance, with calculation of equivalent loss in film thickness.

Specifications

Color	Black
Thickness	10 mil 0.25 mm
Size	6-1/2 x 17 in 165 x 432 mm
Quantity per Box	100
Boxes per Case	5
International Standards	ASTM D 2486 ASTM D 3450 ASTM D 4213 ASTM D 4828 ASTM D 6900 ASTM D 7190 ASTM D 7377 ISO 11998