

SILCO GLIDE T - 57

Product Description:

Silicone based high performance slip and levelling additive for industrial solventbased and UV coating systems.

Technical Data:

form supplied	: clear liquid
active ingredient	: modified polysiloxane
active content	: >98%
solvents	: none
ionic character	: nonionic
pH-Value	: not applicable
Processing	: The additive is added with stirring to the coating formulation
Dosage	: 0.05 – 0.2% based on the whole formulation. Predilution in aliphatic and aromatic solvents is recommended in SB systems

Properties:

SILCO GLIDE T-57 is used as unique slip, mar & levelling additive for SB and UV coating systems like

- * radical cured UV inks and OPV
- * NC or PU based coatings
- * SB 2K automotive coatings

in order to

- * improve wetting/compatibility
- * increase the surface slip
- * improve mar resistance
- * improve gloss/levelling
- * minimize surface defects

Storage:

SILCO GLIDE T-57 is stable for at least two years at room temperature. Please avoid temperatures under 0°C and over 50°C.

FDA-/BfR-Rules:

FDA	: please contact us
BfR	: please contact us

Transport Classifications:

ADR.	: refer to the MSDS
IMCO	: refer to the MSDS
UN-NR	: refer to the MSDS

EEC-Labeling Requirements:

Symbol	: refer to the MSDS
R-S	: refer to the MSDS
S-S	: refer to the MSDS

Packaging:

- small sizes on demand
- 30 kg hobbock
- 200 kg drums
- 1000 kg container

This leaflet gives the user guidance and information but does not claim to be complete and is without any obligation.

Revision: 1/DL
Issue date: 02.May 2011