



# STEEL SURFACE ROUGHNESS COMPARATOR LD2040, LD2050

**DATASHEET** 

## **PRODUCT DESCRIPTION**

Comparison standard according to ISO 8503 part 1 made of quality steel. Indicates the surface condition of blasted steel according to ISO 8503 in grades of fine, medium, and coarse.

## **BUSINESS**

Protective Coatings, Corrosion Control, Surface Finishing, Powder Coating



### **STANDARDS**

ASTM D4417 Method A, ISO 8503-1, ISO 8503-2

# **FEATURES**

- High purity nickel reference plates
- Electro formed profile
- Each profile copied from a certified mild steel master
- Sturdy leather wallet to protect the test surfaces when not in use
- Available for shot- and grit blasting

## **SCOPE OF SUPPLY**

- Steel surface roughness comparator
- Sturdy leather pouch

# **ORDERING INFORMATION**

LD2040 – TQC Steel surface roughness comparator Grit LD2050 - TQC Steel surface roughness comparator Shot

# **SPECIFICATIONS**

LD2040 Surface Roughness Comparator for Grit Blasting LD2050 Surface Roughness Comparator for Shot Blasting

The Netherlands

Material: High purity nickel

Width: 85mm Height: 85mm

The comparator has been reproduced from a specially prepared and numbered master block.

TQC B.V. Molenbaan 19 2908 LL Capelle aan den IJssel

phone: +31 (0)10-7900100 fax: +31 (0)10-7900129 e-mail: info@tqc.eu www.tqc.eu





### **USE**

By placing the appropriate comparator (G for Grit, S for Shot) against a blast cleaned surface, the finish achieved can be compared against the four sections of the comparator. It is then a simple matter to identify (by sight and touch) the standard surface:

- Fine grade equal to or above segment 1 but below segment 2
- Medium grade equal to or above segment 2 but below segment 3
- Coarse grade equal to or above segment 3 but below segment 4

## **SPECIAL CARE**

Always keep the instrument in its pouch when not in use.

#### **DISCLAIMER**

The right of technical modifications is reserved.

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.